



TECHNICAL DATA SHEET

Doküman No	KK.CRT.02
Yayın Tarihi	10.07.2023
Revizyon No	00
Revizyon Tarihi	000
Sayfa	1/1

Product Name : SPUNLACE NONWOVEN FABRIC-%10 CV-%90 PES 38 GSM PLAIN

Technical Characteristics	Analysis Method	Unit	Average values		
			Target	Tolerance	
Composition	-	%	% 10 CV	min. 8	max.12
			% 90 Pes	min. 88	max. 92
Basis Weight	WSP 130.1 (ERT 40.3-90)	g/m ²	38	± 10	
Thickness	WSP 120.6 (ERT 30.5-99)	mm	0,52	min.0,42	max.0,62
Tensile Strength at break (Dry)	WSP 110.4 (ERT 20.2-89)	N \ 50 mm	MD	65	min.52
		N \ 50 mm	CD	15	min.12
Breaking Elongation (Dry)	WSP 110.4 (ERT 20.2-89)	%	MD	50	max.60
		%	CD	160	max.192
Tensile Strength at break (Wet)	WSP 110.4 (ERT 20.2-89)	N \ 50 mm	MD	60	min.48
		N \ 50 mm	CD	13	min.10
Breaking Elongation (Wet)	WSP 110.4 (ERT 20.2-89)	%	MD	60	max.72
		%	CD	150	max.180
Liquid Absorbtion Capacity	WSP 010.1 (ERT 10.3-99)	%		1050	min.1000
Total Bacteria	USP 61 EP 2.6.12	CFU/gr		≤10	≤100
Molds and Yeast	USP 61 EP 2.6.12	CFU/gr		≤10	≤10
Total E.Coli/Coliform	USP 61 EP 2.6.12	CFU/gr		0	0

The width of the reel is measured on the reel. The tolerance for width is ± 3 mm for less then 1000 mm.The tolerance for width is ± 10 mm for high then 1000 mm.

Document Issuing Date

27.12.2023

Prepared By

Serap YEŞİLOVA
Quality Control Chief

Qualified Nonwovens
with Innovation

SENOCO TEKSTİL SANAYİ VE TİCARET A.Ş.
Başpınar (Organize) OSB Mah. OSB 5. Bölge 83513 Nolu Caddde No:7 27560 Şehitkamil/GAZİANTEP
Fax:0342 337 49 53

Tel: 0342 337 49 49