



TECHNICAL DATA SHEET

Doküman No	KK.CRT.02
Yayın Tarihi	10.07.2023
Revizyon No	00
Revizyon Tarihi	000
Sayfa	1/1

Product Name : SPUNLACE NONWOVEN FABRIC-%25 CV-%75 PES 42 GSM PLAIN

Technical Characteristics	Analysis Method	Unit	Average values		
				Target	Tolerance
Composition	-	%		% 25 Cv	min. 22,5 max. 27,5
				% 75 Pes	min. 72,5 max. 77,5
Basis Weight	WSP 130.1 (ERT 40.3-90)	g/m ²		42	± 10
Thickness	WSP 120.6 (ERT 30.5-99)	mm		0,59	min.0,49 max.0,69
Tensile Strength at break (Dry)	WSP 110.4 (ERT 20.2-89)	N \ 50 mm	MD	74	min.60
		N \ 50 mm	CD	25	min.20
Breaking Elongation (Dry)	WSP 110.4 (ERT 20.2-89)	%	MD	50	max.60
		%	CD	160	max.200
Tensile Strength at break (Wet)	WSP 110.4 (ERT 20.2-89)	N \ 50 mm	MD	64	min.52
		N \ 50 mm	CD	20	min.16
Breaking Elongation (Wet)	WSP 110.4 (ERT 20.2-89)	%	MD	60	max.72
		%	CD	150	max.180
Liquid Absorbtion Capacity	WSP 010.1 (ERT 10.3-99)	%		1050	min.1000

The width of the reel is measured on the reel. The tolerance for width is ± 3 mm for less then 1000 mm.The tolerance for width is ± 10 mm for high then 1000 mm.

Document Issuing Date

Prepared By

5.12.2023

Serap YEŞİLOVA
Quality Control Chief

Qualified Nonwovens
with Innovation

SENOCO TEKSTİL SANAYİ VE TİCARET A.Ş.
Başpınar (Organize) OSB Mah. OSB 5. Bölge 83513 Nolu Cadde No:7 27560 Şehitkamil/GAZİANTEP
Fax:0342 337 49 53

Tel: 0342 337 49 49